

A=May be used for
Continuous Service
B=May be used for
Intermittent Service
X=Do not Use
I=Insufficient Data



Chemical	Temperature	UHMWPE	EPDM
Acetaldehyde	100	B	A
Acetic Acid, Conc.	100	A	A
Acetic Acid, Dilute 10	150	B	A
Acetic Acid, Glacial	100	A	A
Acetic Aldehyde	100	A	A
Acetic Anhydride	100	B	A
Acetic Ester	100	B	A
Acetic Ether	100	B	A
Acetic Oxide	100	B	A
Acetone	100	A	A
Acetone Cyanohydrin	100	B	A
Acetyl Acetone	100	B	I
Acetyl Chloride	100	B	B
Acetyl Oxide	100	B	A
Acetylene	100	A	A
Acetylene Dichloride	100	B	I
Acetylene Tetrachloride	100	B	I
Acrolein	100	B	I
Acrylic Acid	100	B	X
Acrylonitrile	100	B	X
Alk-tri	100	I	I
Allyl Alcohol	100	A	A
Allyl Bromide	100	B	I
Allyl Chloride	100	B	X
Alum	150	A	A
Aluminum Acetate	100	A	A
Aluminum Chloride	150	A	A
Aluminum Formate	100	A	I
Aluminum Hydroxide	150	A	A
Aluminum Sulfate	150	A	A
Aminoethanol	100	A	I
Aminoethylethanolamine	100	A	I
Ammonia*			
Ammonia Cupric Sulfate	150	A	A
Ammonium Chloride	150	A	A
Ammonium Hydroxide	150	A	X
Ammonium Nitrate	150	A	A
Ammonium Phosphate	150	A	A
Ammonium Sulfate	150	A	A
Ammonium Sulfide	150	A	A
Ammonium Sulfite	150	A	A

* NO HOSE RECOMMENDED FOR THIS APPLICATION
** SPECIAL HOSE REQUIRED

Source: Goodyear Hose Products,
Industrial Hydraulic Hose Catalog

A=May be used for
Continuous Service
B=May be used for
Intermittent Service
X=Do not Use
I=Insufficient Data



Chemical	Temperature	UHMWPE	EPDM
Ammonium Thiosulfate	100	A	A
Amyl Acetate	100	A	B
Amyl Alcohol	100	A	A
Amyl Chloride	100	A	X
Amyl Oleate	100	A	I
Amyl Phenol	100	A	I
Amyl Phthalate	100	A	I
Amylamine	100	A	X
Anethole	100	X	I
Anhydrous Ammonia*			
Aniline	100	A	A
Animal Grease	100	A	X
Animal Oils	100	A	X
Antimony Pentachloride	100	A	X
Aqua Ammonia	150	A	B
Aromatic Spirits	100	A	X
Aromatic Tar	100	A	X
Arquads	100	A	A
Arsenic Acid	100	A	A
Arsenic Chloride	100	I	X
Arsenic Trichloride	100	I	X
Asphalt**			
ASTM #1 Oil	100	A	X
ASTM #2 Oil	100	A	X
ASTM #3 Oil	100	A	X
Barium Carbonate	100	A	A
Barium Chloride	150	A	A
Barium Hydroxide	150	A	A
Barium Sulfate	150	A	A
Barium Sulfide	150	A	A
Benzal Chloride	100	A	I
Benzaldehyde	100	A	B
Benzene (Benzol)	100	I	X
Benzine (Ligroin)	100	A	X
Benzine Solvent (Ligroin)	100	A	X
Benzoic Acid	100	A	B
Benzoic Aldehyde	100	A	B
Benzotrighloride	100	X	X
Benzoyl Chloride	100	X	X
Benzyl Acetate	100	A	I
Benzyl Alcohol	100	A	X

* NO HOSE RECOMMENDED FOR THIS APPLICATION
** SPECIAL HOSE REQUIRED

Source: Goodyear Hose Products,
Industrial Hydraulic Hose Catalog

A=May be used for
Continuous Service
B=May be used for
Intermittent Service
X=Do not Use
I=Insufficient Data



Chemical	Temperature	UHMWPE	EPDM
Benzyl Chloride	100	A	X
Bichromate of Soda	150	A	I
Black Sulfate Liquor	150	X	B
Black Sulfate Liquor	275	X	X
Bleach	100	A	A
Brine	150	X	A
Bromine	100	B	X
Bromo Benzene	100	X	X
Bromo Toluene	100	X	X
Bromochloromethane	100	B	I
Bunker C.	100	B	X
Bunker Oil	100	A	X
Butanol	100	A	A
Butyl (Normal) Alcohol	100	A	A
Butyl (Secondary) Alcohol	100	A	A
Butyl Acetate	100	A	B
Butyl Acetoacetate	100	A	I
Butyl Acrylate	100	B	X
Butyl Alcohol	100	A	A
Butyl Aldehyde	100	A	X
Butyl Amine	100	A	X
Butyl Benzene	100	A	X
Butyl Benzl Phthalate	100	A	I
Butyl Bromide	100	B	X
Butyl Butyrate	100	B	I
Butyl Carbitol	100	A	B
Butyl Cellosolve	100	A	A
Butyl Chloride	100	B	I
Butyl Ether	100	A	X
Butyl Ethyl Acetaldehyde	100	A	I
Butyl Ethyl Ether	100	A	X
Butyl Phthalate	100	A	I
Butyl Stearate	100	A	X
Butylate	100	A	A
Butyraldehyde	100	A	X
Butyric Acid	100	A	B
Butyric Anhydride	100	A	I
Cadmium Acetate	100	A	I
Calcium Acetate	100	A	A
Calcium Aluminate	100	A	A
Calcium Bichromate	150	X	I

* NO HOSE RECOMMENDED FOR THIS APPLICATION
** SPECIAL HOSE REQUIRED

Source: Goodyear Hose Products,
Industrial Hydraulic Hose Catalog

A=May be used for
Continuous Service
B=May be used for
Intermittent Service
X=Do not Use
I=Insufficient Data



Chemical	Temperature	UHMWPE	EPDM
Calcium Bisulfate	150	A	A
Calcium Bisulfite	150	A	A
Calcium Carbonate	150	A	A
Calcium Chloride	150	A	A
Calcium Hydroxide	100	A	A
Calcium Hypochlorite	100	B	B
Calcium Nitrate	150	A	A
Calcium Silicate	150	A	A
Calcium Sulfate	150	A	A
Calcium Sulphhydrate	100	A	A
Calcium Sulfide	150	A	A
Calcium Sulfite	150	A	A
Caprylic Acid	100	A	I
Carbitol	100	A	A
Carbitol Acetate	100	A	I
Carbolic Acid, Phenol	100	A	X
Carbon Dioxide	100	A	A
Carbon Disulfide*			
Carbon Tetrachloride	100	B	X
Carbonic Acid	100	A	A
Casinghead Gasoline	100	B	X
Castor Oil	100	A	A
Caustic Potash	150	A	B
Caustic Soda	150	A	A
Cellosize	100	A	I
Cellosolve	100	A	A
Cellosolve	100	A	B
Cellosolve Acetate	100	A	X
Chloracetic Acid	100	A	X
Chlorinated Solvents	100	B	X
Chlorine (Dry) *			
Chlorine (Wet)	100	X	X
Chloroacetone	100	A	X
Chlorobenzene	100	B	X
Chlorobenzol	100	A	X
Chlorobutane	100	X	I
Chloroethylbenzene	100	A	X
Chloroform	100	B	X
Chloropentane	100	A	X
Chlorophenol	100	A	X
Chloropropanone	100	A	X

* NO HOSE RECOMMENDED FOR THIS APPLICATION
** SPECIAL HOSE REQUIRED

Source: Goodyear Hose Products,
Industrial Hydraulic Hose Catalog

A=May be used for
Continuous Service
B=May be used for
Intermittent Service
X=Do not Use
I=Insufficient Data



Chemical	Temperature	UHMWPE	EPDM
Chlorosulfonic Acid	100	X	X
Chlorothene	100	X	X
Chlorotoluene	100	X	X
Chlorpyrifos	100	I	X
Chromic Acid 25%	100	B	X
Coal Oil	100	A	X
Coal Tar	100	A	X
Coal Tar Naphtha	100	A	X
Copper Chloride	100	A	A
Copper Hydrate	100	A	I
Copper Hydroxide	100	A	I
Copper Nitrate	100	A	A
Copper Nitrite	100	A	A
Copper Sulfate	100	A	A
Copper Sulfide	100	A	A
Creosols	100	A	X
Creosote	100	A	X
Cresylic Acid	100	A	X
Crotonaldehyde	100	A	I
Crude Oil	100	A	X
Cumene	100	A	X
Cupric Carbonate	100	A	A
Cupric Chloride	100	A	A
Cupric Nitrate	100	A	A
Cupric Nitrite	100	A	A
Cupric Sulfate	100	A	A
Cyclohexane	100	A	X
Cyclohexanol	100	A	X
Cyclohexanone	100	A	X
Cyclopentane	100	A	X
Cyclopentane, methyl	100	A	X
Cyclopentanol	100	A	X
Cyclopentanone	100	A	X
DDT in Kerosene	100	A	X
DMP	100	X	X
Decalin	100	X	X
Decanol	100	A	A
Decyl Alcohol	100	A	A
Decyl Aldehyde	100	A	I
Decyl Butyl Phthalate	100	A	I
Denatured Alcohol	100	A	A

* NO HOSE RECOMMENDED FOR THIS APPLICATION
** SPECIAL HOSE REQUIRED

Source: Goodyear Hose Products,
Industrial Hydraulic Hose Catalog

A=May be used for
Continuous Service
B=May be used for
Intermittent Service
X=Do not Use
I=Insufficient Data



Chemical	Temperature	UHMWPE	EPDM
Diacetone Alcohol	100	A	X
Diamyl Phenol	100	A	X
Diamylamine	100	A	I
Diamylene	100	A	X
Dibenzyl Ether	100	A	X
Dibromobenzene	100	B	X
Dibutyl Amine	100	A	X
Dibutyl Ether	100	A	X
Dibutyl Phthalate	100	A	A
Dibutyl Sebacate	100	A	X
Dicalcium Phosphate	100	A	A
Dicamba	100	A	A
Dichloroacetic Acid	100	A	I
Dichlorobenzene	100	A	X
Dichlorobutane	100	A	X
Dichlorodifluoromethane	100	I	X
Dichloroethane	100	A	X
Dichloroethyl Ether	100	A	X
Dichloroethylene	100	X	I
Dichlorohexane	100	A	X
Dichloromethane	100	A	X
Dichloropentane	100	A	X
Dichloropropane	100	A	X
Diesel Oil	150	A	X
Diethanol Amine	100	A	I
Diethyl Benzene	100	A	X
Diethyl Carbinol	100	A	I
Diethyl Ketone	100	A	X
Diethyl Oxalate	100	A	X
Diethyl Phthalate	100	A	X
Diethyl Sebacate	100	A	X
Diethyl Sulfate	100	A	I
Diethyl Triamine	100	A	I
Diethylamine	100	A	B
Diethylene Dioxide	100	A	A
Diethylene Glycol	100	A	A
Diethylene Triamine	100	A	I
Dihydroxydiethyl Ether	100	A	A
Dihydroxyethyl Amine	100	A	I
Diisobutyl Ketone	100	A	B
Diisobutylene	100	A	X

* NO HOSE RECOMMENDED FOR THIS APPLICATION
** SPECIAL HOSE REQUIRED

Source: Goodyear Hose Products,
Industrial Hydraulic Hose Catalog

A=May be used for
Continuous Service
B=May be used for
Intermittent Service
X=Do not Use
I=Insufficient Data



Chemical	Temperature	UHMWPE	EPDM
Diisooctyl Adipate	100	A	I
Diisooctyl Phthalate	100	A	I
Diiosocyanate	100	A	X
Diisodecyl Adipate	100	A	I
Diisodecyl Phthalate	100	A	I
Diisopropanol Amine	100	A	I
Diisopropyl Amine	100	A	I
Diisopropyl Ether	100	A	X
Diisopropyl Ketone	100	A	B
Dilauryl Ether	100	A	I
Dimethyl Amine		A	
Dimethyl Benzene	100	A	X
Dimethyl Ether	100	A	X
Dimethyl Ketone	100	A	A
Dimethyl Phenol	100	A	X
Dimethyl Phthalate	100	A	B
Dimethyl Sulfate	100	A	I
Dimethyl Sulfide *			
Dimethyl Carbinol	100	A	A
Dinitrobenzene	100	A	I
Diocetyl Adipate	100	A	B
Diocetyl Amine	100	A	I
Diocetyl Phthalate	100	A	X
Diocetyl Sebacate	100	A	B
Dioxane	100	A	X
Dioxolane	100	A	X
Diphenyl Phthalate	100	A	I
Dipropyl Ketone	100	A	I
Dipropylamine	100	A	I
Dipropylene Glycol	100	A	I
Disodium Phosphophate	100	A	I
Divinyl Benzene	100	A	X
Dodecyl Benzene	100	A	X
Dodecyl Toluene	100	A	X
Dow-Per	100	A	X
Dowtherm A	100	A	X
Dowtherm E	100	A	X
Dowtherm SR-1	100	A	I
Endolene	100	I	I
Epichlorohydrate	100	A	X
Ethanol	100	A	A

* NO HOSE RECOMMENDED FOR THIS APPLICATION
** SPECIAL HOSE REQUIRED

Source: Goodyear Hose Products,
Industrial Hydraulic Hose Catalog

A=May be used for
Continuous Service
B=May be used for
Intermittent Service
X=Do not Use
I=Insufficient Data



Chemical	Temperature	UHMWPE	EPDM
Ethanol Amine	100	A	B
Ethyl Acetate	100	A	A
Ethyl Acetoacetate	100	A	B
Ethyl Acrylate	100	A	X
Ethyl Alcohol	100	A	A
Ethyl Aldehyde*			
Ethyl Aluminum Dichloride	100	X	X
Ethyl Benzene	100	A	X
Ethyl Butanol	100	A	A
Ethyl Butyl Acetate	100	A	I
Ethyl Butyl Alcohol	100	A	A
Ethyl Butyl Amine	100	A	I
Ethyl Butyl Ketone	100	A	I
Ethyl Butyraldehyde	100	A	I
Ethyl Chloride*			
Ethyl Dichloride	100	B	X
Ethyl Ether*			
Ethyl Formate	100	A	B
Ethyl Hexanol	100	A	A
Ethyl Hexoic Acid	100	A	I
Ethyl Hexyl Acetate	100	A	I
Ethyl Hexyl Alcohol	100	A	A
Ethyl Iodide	100	X	X
Ethyl Isobutyl Ether	100	A	X
Ethyl Mewthyl Ketone	100	A	I
Ethyl Oxalate	100	A	X
Ethyl Phthalate	100	A	I
Ethyl Propyl Ether	100	A	X
Ethyl Propyl Ketone	100	A	I
Ethyl Silicate	100	A	I
Ethyl Sulfate	100	A	I
Ethylamine*			
Ethylene Bromide	100	X	X
Ethylene Chloride	100	B	X
Ethylene Diamine	100	A	B
Ethylene Dibromide	100	X	X
Ethylene Dichloride	100	B	X
Ethylene Glycol	150	B	A
Ethylhexil Phosphorodieth	100	A	X
Ex-Tri	100	I	I
Ferric Bromide	150	A	A

* NO HOSE RECOMMENDED FOR THIS APPLICATION
** SPECIAL HOSE REQUIRED

Source: Goodyear Hose Products,
Industrial Hydraulic Hose Catalog

A=May be used for
Continuous Service
B=May be used for
Intermittent Service
X=Do not Use
I=Insufficient Data



Chemical	Temperature	UHMWPE	EPDM
Ferric Chloride	150	A	A
Ferric Sulfate	150	A	A
Ferrous Acetate	100	A	I
Ferrous Chloride	150	A	A
Ferrous Hydroxide	100	A	I
Ferrous Sulfate	150	A	A
Fluoboric Acid 65%	150	B	I
Fluorine (wet)	100	X	X
Fluosilicic Acid 50%	150	B	I
Formaldehyde 40%	100	A	A
Formalin	100	A	A
Formic Acid	100	A	A
Freon 12	100	A	X
Freon 22	100	A	I
Fuel A (ASTM)	100	B	X
Fuel B (ASTM)	100	B	X
Fuel Oil	100	A	X
Furfural	100	A	B
Furfuryl Alcohol	100	A	I
Gallic Acid	100	A	B
Gasoline	100	B	X
Glacial Acetic Acid	100	A	A
Gluconic Acid	100	A	I
Glycerin	100	A	A
Glyphosate	100	A	A
Graffinite	100	I	X
Grease	100	A	X
Green Sulfate Liquor	150	A	A
Heptanal	100	A	I
Heptane	100	A	X
Heptane Carboxylic Acid	100	A	I
Hexaldehyde	100	A	X
Hexane	100	B	X
Hexanol	100	A	A
Hexyl Methyl Ketone	100	A	I
Hexylamine	100	A	I
Hexylene	100	X	X
Hexylene Glycol	150	A	I
Hexyl-Alcohol	100	A	X
Hi-Tri	100	A	X
Hydrochloric Acid 38%	125	I	B

* NO HOSE RECOMMENDED FOR THIS APPLICATION
** SPECIAL HOSE REQUIRED

Source: Goodyear Hose Products,
Industrial Hydraulic Hose Catalog

A=May be used for
Continuous Service
B=May be used for
Intermittent Service
X=Do not Use
I=Insufficient Data



Chemical	Temperature	UHMWPE	EPDM
Hydrobromic Acid 37%	150	B	A
Hydrochloric Acid 37%	125	A	B
Hydrofluoric Acid 10%	125	A	I
Hydrofluosilicic Acid	150	B	A
Hydrogen Dioxide 10%	100	B	I
Hydrogen Dioxide over 10%	100	B	X
Hydrogen Gas	100	A	A
Hydrogen Peroxide 10% to 50%	100	B	I
Hydrogen Peroxide over 50%	100	X	X
Iodine	100	A	I
Iron Acetate	100	A	I
Iron Hydroxide	100	A	I
Iron Salts	150	A	A
Iron Sulfate	150	A	A
Iron Sulfide	150	A	A
Isoamyl Acetate	100	A	X
Isoamyl Alcohol	100	A	A
Isoamyl Bromide	100	B	X
Isoamyl Butyrate	100	B	I
Isoamyl Chloride	100	X	I
Isoamyl Ether	100	A	X
Isoamyl Phthalate	100	A	I
Isobutane*			
Isobutanol	100	A	A
Isobutyl Acetate	100	A	X
Isobutyl Alcohol	100	A	A
Isobutyl Aldehyde	100	A	I
Isobutyl Amine	100	A	I
Isobutyl Bromide	100	B	X
Isobutyl Carbinol	100	A	A
Isobutyl Chloride	100	B	X
Isobutyl Ether	100	A	X
Isobutylene	100	A	X
Isooctane	100	B	X
Isopentane*			
Isophorone	100	B	A
Isopropanol	100	A	A
Isopropanol Amine	100	A	I
Isopropyl Acetate	100	A	X
Isopropyl Alcohol	100	A	A
Isopropyl Amine	100	A	I

* NO HOSE RECOMMENDED FOR THIS APPLICATION
** SPECIAL HOSE REQUIRED

Source: Goodyear Hose Products,
Industrial Hydraulic Hose Catalog

A=May be used for
Continuous Service
B=May be used for
Intermittent Service
X=Do not Use
I=Insufficient Data



Chemical	Temperature	UHMWPE	EPDM
Isopropyl Benzene	100	A	X
Isopropyl Chloride*			
Isopropyl Ether	100	A	X
Isopropyl Toluene	100	A	X
Jet Fuels**			
Kerosene	100	A	X
Lauryl Alcohol	100	A	A
Lead Acetate	100	A	B
Lead Sulfate	150	A	A
Ligroin	100	A	X
Linseed Oil	100	A	B
Liquefied Natural Gas*			
Liquefied Petroleum Gas*			
Lubricating Oils	100	A	X
MIBK	100	A	X
MEK	100	A	X
Magnesium Acetate	100	A	I
Magnesium Chloride	150	A	A
Magnesium Hydrate	150	A	I
Magnesium Hydroxide	150	A	A
Magnesium Sulfate	150	A	B
Maleic Acid	100	A	I
Malic Acid	150	B	I
Manganese Sulfate	150	A	A
Manganese Sulfide	150	A	A
Manganese Sulfite	150	A	A
Menthanol	100	A	A
Mesityl Oxide	100	A	X
Methallyl Alcohol	100	A	A
Methyl Alcohol	100	A	A
Methyl Acetate	100	A	A
Methyl Acetoacetate	100	A	I
Methyl Acetone*			
Methyl Amyl Acetate	100	B	X
Methyl Amyl Alcohol	100	A	A
Methyl Amyl Carbinol	100	A	A
Methyl Amyl Ketone	100	A	I
Methyl Benzene	100	A	X
Methyl Butanol	100	A	I
Methyl Butanone	100	A	B
Methyl Butyl Ketone	100	A	I

* NO HOSE RECOMMENDED FOR THIS APPLICATION
** SPECIAL HOSE REQUIRED

Source: Goodyear Hose Products,
Industrial Hydraulic Hose Catalog

A=May be used for
Continuous Service
B=May be used for
Intermittent Service
X=Do not Use
I=Insufficient Data



Chemical	Temperature	UHMWPE	EPDM
Methyl Carbitol	100	A	I
Methyl Cellosolve	100	A	A
Methyl Chloride*			
Methyl Cyclohexane	100	A	X
Methyl Ethyl Ketone	100	A	B
Methyl Hexanol	100	A	A
Methyl Hexanone	100	A	I
Methyl Hexyl Ketone	100	A	I
Methyl Isobutyl Carbinol	100	A	A
Methyl Isobutyl Ketone	100	A	B
Methyl Iropropyl Ketone	100	A	B
Methyl Normal Amyl Ketone	100	A	I
Methyl Propyl Carbinol	100	A	A
Methyl Propyl Ether	100	A	X
Methyl Propyl Ketone	100	A	I
Methyl Tertiary Butyl Ether 100%	100	X	X
Methylallyl Acetate	100	A	A
Methylallyl Chloride	100	A	I
Methyldiethanolamine	100	A	X
Methylene Bromide	100	B	X
Methylene Chloride*			
Metribuzin	100	A	A
Mineral Spirits	100	A	X
Monochloroacetic Acid	100	A	X
Monochlorobenzene	100	B	X
Monochlorodifluoromethane	100	I	I
Monoethanol Amine	100	A	B
Monethyl Amine*			
Monoisopropanol Amine	100	A	I
Muriatic Acid	125	A	X
N/Methylpyrrolidone	100	A	X
Naphtha	100	A	X
Naphthalene	100	A	X
Natural Gas*			
Neohexane	100	A	X
Neu-Tri	150	A	X
Nickel Chloride	150	A	A
Nickel Nitrate	150	A	A
Nickel Sulfate	100	A	A
Nitric Acid 25%	100	B	X
Nitric Acid 37%	100	X	X

* NO HOSE RECOMMENDED FOR THIS APPLICATION
** SPECIAL HOSE REQUIRED

Source: Goodyear Hose Products,
Industrial Hydraulic Hose Catalog

A=May be used for
Continuous Service
B=May be used for
Intermittent Service
X=Do not Use
I=Insufficient Data



Chemical	Temperature	UHMWPE	EPDM
Nitric Acid 40-46%	100	X	X
Nitric Acid 70%	100	X	X
Nitro Benzene	100	A	X
Nitrogen Gas	100	A	A
Nitrous Oxide	100	A	A
Nonenes	100	A	X
Octadecanoic Acid	100	B	B
Octane	100	A	X
Octanol	100	A	X
Octyl Acetate	100	A	I
Octyl Alcohol	100	A	X
Octyl Aldehyde	100	A	I
Octyl Amine	100	A	I
Octyl Carbinol	100	A	A
Octylene Glycol	100	A	A
Oil Petroleum	100	B	X
Oleic Acid	100	A	X
Oleum	100	X	X
Organic Fatty Acids	100	A	X
Orthodichlorobenzene	100	A	X
Orthodichlorobenzol	100	A	X
Orthoxylene	100	B	X
Oxalic Acid	100	A	B
Oxygen*			
Ozone	100	A	A
Palmitic Acid	100	A	B
Papermakers Alum	150	A	A
Paradichlorobenzol	100	B	X
Paraffin	150	A	X
Paraldehyde	100	A	B
Paraxylene	100	A	X
Pelargonic Acid	100	A	I
Pentachloroethane	100	A	X
Pentane	100	X	X
Pentanol	100	A	A
Pentanone	100	A	I
Perchloroethylene	100	B	X
Petroleum Ether (Ligroin)	100	A	X
Petroleum -Crude	100	A	X
Petroleum Oils	100	A	X
Phenol	125	A	X

* NO HOSE RECOMMENDED FOR THIS APPLICATION
** SPECIAL HOSE REQUIRED

Source: Goodyear Hose Products,
Industrial Hydraulic Hose Catalog

A=May be used for
Continuous Service
B=May be used for
Intermittent Service
X=Do not Use
I=Insufficient Data



Chemical	Temperature	UHMWPE	EPDM
Phenolsulfonic Acid	100	X	I
Phenyl Chloride	100	A	X
Phosphoric Acid 10%	150	A	A
Phosphoric Acid 10-85%	100	A	A
Pine Oil	100	A	X
Pinene	100	A	X
Polethylene Glycol	150	A	A
Polypropylene Glycol	150	A	A
Potassium Acetate	100	A	B
Potassium Bisulfate	150	A	A
Potassium Bisulfite	150	A	A
Potassium Carbonate	150	A	A
Potassium Chloride	150	B	A
Potassium Chromate	150	B	I
Potassium Dichromate	150	A	I
Potassium Hydrate	150	B	B
Potassium Hydroxide	150	A	B
Potassium Nitrate	150	A	A
Potassium Permanganate	100	A	I
Potassium Silicate	150	A	A
Potassium Sulfate	150	A	A
Potassium Sulfide	150	A	A
Potassium Sulfite	150	A	A
Propanediol	100	A	A
Propane Gas*			
Propanol	100	A	A
Propyl Acetate	100	A	X
Propyl Alcohol	100	A	A
Propyl Aldehyde	100	A	I
Propyl Chloride*			
Propylene Diamine	100	A	I
Propylene Dichloride	100	B	X
Propylene Glycol	100	A	A
Propylene Tetramer	100	A	X
Sea Water	100	A	A
Sewage	100	A	A
Silicate of Soda	100	A	A
Soap	100	A	X
Soda Ash	100	A	A
Soda, Caustic	100	A	A
Soda, Lime	100	A	A

* NO HOSE RECOMMENDED FOR THIS APPLICATION
** SPECIAL HOSE REQUIRED

Source: Goodyear Hose Products,
Industrial Hydraulic Hose Catalog

A=May be used for
Continuous Service
B=May be used for
Intermittent Service
X=Do not Use
I=Insufficient Data



Chemical	Temperature	UHMWPE	EPDM
Soda, Niter	100	A	B
Sodium Acetate	100	A	B
Sodium Aluminate	100	A	A
Sodium Bisulfate	150	A	A
Sodium Bisulfite	150	A	A
Sodium Carbonate	150	A	A
Sodium Chloride (Brine)	150	A	A
Sodium Chromate	150	X	I
Sodium Dichromate	150	A	A
Sodium Hydrate	150	A	A
Sodium Hydrochlorite 20%	100	A	I
Sodium Hydrosulfide	100	A	X
Sodium Hydroxide 50%	150	A	A
Sodium Hypochlorite	100	B	A
Sodium Ntrate	150	A	B
Sodium Silicate	150	A	A
Sodium Sulfate	150	A	A
Sodium Sulfide	150	A	A
Sodium Sulfite	150	A	B
Sodium Sulphydrate	100	A	X
Sodium Thiosulfate	150	A	A
Stannic Chloride	150	A	A
Stannic Sulfide	150	A	A
Stannous Chloride	150	A	B
Stannous Sulfide	150	A	A
Stearic Acid	100	A	B
Stoddards Solvent	100	A	X
Styrene	100	B	X
Sulfamic Acid >10%	100	X	I
Sulfonic Acid	100	B	I
Sulfur Dioxide (Liquid)	100	B	I
Sulfuric Acid 25%	150	A	A
Sulfuric Acid 93%	100	X	B
Sulfuric Acid 93-98%	100	X	X
Sulfuric Acid Fuming	100	X	X
Sulfurous Acid 10%	150	A	A
Sulfurous Acid 10-75%	100	A	A
Sulphonate	100	I	X
Tall Oil	100	A	X
Tallow	150	A	X
Tannic Acid	150	A	X

* NO HOSE RECOMMENDED FOR THIS APPLICATION
** SPECIAL HOSE REQUIRED

Source: Goodyear Hose Products,
Industrial Hydraulic Hose Catalog

A=May be used for
Continuous Service
B=May be used for
Intermittent Service
X=Do not Use
I=Insufficient Data



Chemical	Temperature	UHMWPE	EPDM
Tar**			
Tartaric Acid	150	A	A
Tergitol	100	X	I
Tertiary Butyl Alcohol	100	A	A
Tetrachlorobenzene	100	B	X
Tetrachloroethane	100	A	X
Tetrachloroethylene	100	A	X
Tetrachloromethane	100	A	X
Tetrachloronaphthalene	100	B	X
Tetradecanol	100	A	A
Tetraethylene Glycol	150	A	A
Tetraethylene Lead	100	X	X
Tetrahydrofuran	100	B	X
THF	100	B	X
Thionyl Chloride	100	X	I
Tin Chloride	100	A	A
Tin Tetrachloride	150	B	A
Titanium Tetrachloride	100	B	X
Toluene	100	A	X
Toluidine	100	X	I
Toluol	100	A	X
Transformer Oil	100	X	I
Transmission Oil "A"	150	B	X
Tributoxy Ethylsulphate	100	I	A
Tributyl Amine	100	A	I
Tributyl Phosphate	100	A	X
Trichlorobenzene	100	B	X
Trichloroethane	100	A	X
Trichloroethylene	100	X	X
Trichloropropane	100	A	X
Tricresylphosphate	100	A	A
Tridecanol	100	A	A
Triethanolamine	100	A	A
Triethylamine	100	A	I
Triethylene Glycol	150	A	I
Trifluralin (Trefalin)	100	A	X
Triphenyl Phosphate	100	A	I
Tripolyphosphate	100	X	I
Trisodium Phosphate	150	A	A
Turpentine	100	A	X
Urea	100	A	I

* NO HOSE RECOMMENDED FOR THIS APPLICATION
** SPECIAL HOSE REQUIRED

Source: Goodyear Hose Products,
Industrial Hydraulic Hose Catalog

A=May be used for
Continuous Service
B=May be used for
Intermittent Service
X=Do not Use
I=Insufficient Data



Chemical	Temperature	UHMWPE	EPDM
Undecanol	100	B	A
VM &P Naphtha	100	A	X
Vinyl Acetate	100	A	X
Vinyl Benzene	100	A	X
Vinyl Chloride*			
Vinyl Ether*			
Vinyl Toluene	100	A	X
Vinyl Trichloride	100	A	X
Water	180	A	A
Wax	100	A	X
White Oil	100	A	X
Wood Alcohol	100	A	A
Xylene (Xylol)	100	X	X
Xylidine	100	B	X
Zinc Carbonate	150	A	A
Zinc Chloride	150	A	A
Zinc Chromate	150	A	X
Zinc Phosphate	100	A	A
Zinc Sulfate	150	A	A

* NO HOSE RECOMMENDED FOR THIS APPLICATION
** SPECIAL HOSE REQUIRED

Source: Goodyear Hose Products,
Industrial Hydraulic Hose Catalog

A=May be used for
Continuous Service
B=May be used for
Intermittent Service
X=Do not Use
I=Insufficient Data



LDPE
A
A
A
A
A
A
A
A
A
X
A
A
A
B
A
A
A
A
A
A
X
X
A
A
A
A
A
A
A
A
A
A
A
A
A
A
A
X
B
A
A
A

* NO HOSE RECOMMENDED FOR THIS APPLICATION
** SPECIAL HOSE REQUIRED

Source: Goodyear Hose Products,
Industrial Hydraulic Hose Catalog

A=May be used for
Continuous Service
B=May be used for
Intermittent Service
X=Do not Use
I=Insufficient Data



LDPE
A
A
A
X
X
A
X
X
X
X
A
X
A
A
A
A
A
A
B
A
A
A
A
A
B
B
A
X
B
A
A
A
A
A
A
I
A
A
A
A
A
A
X

* NO HOSE RECOMMENDED FOR THIS APPLICATION
** SPECIAL HOSE REQUIRED

Source: Goodyear Hose Products,
Industrial Hydraulic Hose Catalog

A=May be used for
 Continuous Service
 B=May be used for
 Intermittent Service
 X=Do not Use
 I=Insufficient Data



LDPE
A
I
A
A
A
X
A
A
A
A
A
A
A
A
A
A
A
A
A
A
A
A
A
A
A
A
A
A
A
A
A
A
A
X
A
A
A
X
A
X
A
X
A

* NO HOSE RECOMMENDED FOR THIS APPLICATION
 ** SPECIAL HOSE REQUIRED

Source: Goodyear Hose Products,
 Industrial Hydraulic Hose Catalog

A=May be used for
 Continuous Service
 B=May be used for
 Intermittent Service
 X=Do not Use
 I=Insufficient Data



LDPE
X
A
X
I
X
A
A
A
A
A
A
A
A
A
A
A
A
A
A
A
A
A
A
A
A
A
A
AA
A
A
A
A
A
A
A
A
A
X
A
A
A
A
A

* NO HOSE RECOMMENDED FOR THIS APPLICATION
 ** SPECIAL HOSE REQUIRED

Source: Goodyear Hose Products,
 Industrial Hydraulic Hose Catalog

A=May be used for
Continuous Service
B=May be used for
Intermittent Service
X=Do not Use
I=Insufficient Data



LDPE
A
A
A
A
A
A
A
A
A
A
A
A
A
B
B
A
A
A
A
A
A
A
A
A
A
A
A
A
A
A
A
A
A
A
A
A
A
A
A
A
A
A
A
A
A
A
A
A
A
A
A
I
A
A

* NO HOSE RECOMMENDED FOR THIS APPLICATION
** SPECIAL HOSE REQUIRED

Source: Goodyear Hose Products,
Industrial Hydraulic Hose Catalog

A=May be used for
 Continuous Service
 B=May be used for
 Intermittent Service
 X=Do not Use
 I=Insufficient Data



LDPE
A
A
A
B
A
B
A
A
A
A
I
A
A
B
A
A
A
A
A
A
B
A
A
A
A
A
A
A
A
A
B
B
A
B
B
A
X
A
A

* NO HOSE RECOMMENDED FOR THIS APPLICATION
 ** SPECIAL HOSE REQUIRED

Source: Goodyear Hose Products,
 Industrial Hydraulic Hose Catalog

A=May be used for
Continuous Service
B=May be used for
Intermittent Service
X=Do not Use
I=Insufficient Data



LDPE
A
A
A
A
A
A
A
I
X
I
A
A
B
B
B
B
B
B
B
A
A
I
B
A
A
B
I
X
B
A
A
B
A
A
A
B
A
A
A
X
A
A
A
A

* NO HOSE RECOMMENDED FOR THIS APPLICATION
** SPECIAL HOSE REQUIRED

Source: Goodyear Hose Products,
Industrial Hydraulic Hose Catalog

A=May be used for
Continuous Service
B=May be used for
Intermittent Service
X=Do not Use
I=Insufficient Data



LDPE
I
A
A
I
I
I
A
I
X
B
A
A
A
A
A
A
A
A
B
B
X
A
A
A
A
A
A
A
A
X
A
X
A
A
B
B
A
A
A
A
A
A

* NO HOSE RECOMMENDED FOR THIS APPLICATION
** SPECIAL HOSE REQUIRED

A=May be used for
Continuous Service
B=May be used for
Intermittent Service
X=Do not Use
I=Insufficient Data



LDPE
A
A
A
A
A
A
A
A
A
I
B
B
A
A
A
A
A
A
B
I
A
A
A
A
A
A
A
A
A
A
A
A
A
A
A
A
A
A
A
A

* NO HOSE RECOMMENDED FOR THIS APPLICATION
** SPECIAL HOSE REQUIRED

Source: Goodyear Hose Products,
Industrial Hydraulic Hose Catalog

A=May be used for
Continuous Service
B=May be used for
Intermittent Service
X=Do not Use
I=Insufficient Data



LDPE
A
A
B
B
A
A
A
A
A
A
A
A
A
A
A
A
A
B
A
B
I
A
A
B
I
A
A
A
A
A
A
A
A
A
A
A
B
X

* NO HOSE RECOMMENDED FOR THIS APPLICATION
** SPECIAL HOSE REQUIRED

Source: Goodyear Hose Products,
Industrial Hydraulic Hose Catalog

A=May be used for
Continuous Service
B=May be used for
Intermittent Service
X=Do not Use
I=Insufficient Data



LDPE
B
A
A
A
A
A
A
A
A
A
A
A
A
B
B
A
A
A
A
A
A
A
A
A
A
A
A
A
A
A
B
A
A
A
A
A
A
X
A
A
A

* NO HOSE RECOMMENDED FOR THIS APPLICATION
** SPECIAL HOSE REQUIRED

Source: Goodyear Hose Products,
Industrial Hydraulic Hose Catalog

A=May be used for
Continuous Service
B=May be used for
Intermittent Service
X=Do not Use
I=Insufficient Data



LDPE
A
B
A
A
A
A
A
A
X
A
A
B
A
A
X
A
A
A
A
A
A
A
A
A
A
A
A
A
A
A
A
X
I
B
X
A
A
I
X
A
A
X
I
I
I

* NO HOSE RECOMMENDED FOR THIS APPLICATION
** SPECIAL HOSE REQUIRED

Source: Goodyear Hose Products,
Industrial Hydraulic Hose Catalog

A=May be used for
Continuous Service
B=May be used for
Intermittent Service
X=Do not Use
I=Insufficient Data



LDPE
A
I
A
B
X
A
X
X
A
A
X
B
B
I
A
A
A
B
I
A
I
I
X
A
A
B
X
X
A
A
A
A
A
A
A
A
A
I
A
A
A

* NO HOSE RECOMMENDED FOR THIS APPLICATION
** SPECIAL HOSE REQUIRED

Source: Goodyear Hose Products,
Industrial Hydraulic Hose Catalog

A=May be used for
 Continuous Service
 B=May be used for
 Intermittent Service
 X=Do not Use
 I=Insufficient Data



LDPE
A
A
A
A
A
A
A
X
I
A
A
B
A
A
B
X
A

* NO HOSE RECOMMENDED FOR THIS APPLICATION
 ** SPECIAL HOSE REQUIRED